



Europäisches Patentamt
European Patent Office
Office européen des brevets



⑪ Publication number:

0 461 484 A2

⑫

EUROPEAN PATENT APPLICATION

⑲ Application number: 91108884.7

⑳ Date of filing: 31.05.91

⑤① Int. Cl.⁵: **C08J 7/04**, C09D 127/18,
C09D 129/10, C09D 133/16,
C09D 183/04, //A61L15/00,
C08L101:02, C08L29:04

③① Priority: 01.06.90 JP 144934/90

④③ Date of publication of application:
18.12.91 Bulletin 91/51

⑥④ Designated Contracting States:
DE FR GB

⑦① Applicant: UNITIKA LTD.
No. 50, Higashihonmachi 1-chome
Amagasaki-shi Hyogo(JP)

⑦② Inventor: Umemura, Yoshihiro, c/o Unitika Ltd.
Central Research Institute, 23, Uji Kozakura
Uji-shi, Kyoto(JP)

⑦④ Representative: Hansen, Bernd, Dr.
Dipl.-Chem. et al
Hoffmann, Eitle & Partner Patent- und
Rechtsanwälte Arabellastrasse 4 Postfach
81 04 20
W-8000 München 81(DE)

⑤④ Multi-layered sheet.

⑤⑦ A multi-layered sheet is disclosed, comprising a film substrate or sheet substrate which swells, disperses or dissolves in water, which has a fluorine-type or silicone-type water repellent coated on one side of the substrate.

EP 0 461 484 A2

FIELD OF THE INVENTION

The present invention relates to a multilayered sheet, one side of which is water-impermeable but which as a whole becomes water-dispersible or water-swella-
 5 ble when water comes into contact with the other side of the sheet and penetrates therinto.

BACKGROUND OF THE INVENTION

A known material which is both impermeable to water and which is soluble or dispersible in water is one
 10 which comprises a combination of polyvinyl alcohol and a gelation accelerator for polyvinyl alcohol. Specifically, such a material is composed of a polyvinyl alcohol film having formed thereon an absorption and retention layer constituted by a powder of a highly water-absorptive polymer and a powder of a gelation accelerator for polyvinyl alcohol. A sanitary napkin utilizing this material has been proposed (JP-B-59-13213, corresponding to U.S. Patent 4,333,464). (The term "JP-B" as used herein means an "examined
 15 Japanese patent publication".) This sanitary napkin is considered to function as follows. The gelation accelerator for polyvinyl alcohol dissolves in the water contained in menstrual blood absorbed by the absorption and retention layer, and the resulting aqueous solution of the gelation accelerator wets the polyvinyl alcohol film to form a temporary insoluble gel. Thus, the sanitary napkin can exhibit a leakage preventing effect. When this napkin is immersed in a large quantity of water, the concentration of the
 20 gelation accelerator is lowered and, as a result, the gel collapses and becomes water-soluble or water-dispersible.

In the above-described sanitary napkin, the concentration in menstrual blood of the gelation accelerator for polyvinyl alcohol is an important point in order for the polyvinyl alcohol film to undergo gelation with the aid of the gelation accelerator. Although the range of gelation accelerator concentrations that can cause
 25 gelation varies depending on the kind of the gelation accelerator, it has been difficult with such a system to always and completely prevent the leakage of menstrual blood.

In JP-A-63-181758 (the term "JP-A" as used herein means an "unexamined published Japanese patent application") (corresponding to U.S. Patents 4,762,738, 4,830,187 & 4,930,942), an ostomy pouch is proposed which can be thrown away by means of flushing in an ordinary toilet. This ostomy pouch is
 30 produced by joining a front panel consisting of a water-swella- and cold water-insoluble film material having a water-resistant layer laminated thereto to a rear panel consisting of a water-swella- and cold water-insoluble film material having a layer laminated thereto. Since this ostomy pouch employs water-swella- and cold water-insoluble film materials on the inner side thereof, it becomes viscous upon contact with water in a toilet stool to thereby pass through the drainage piping system.

However, such an ostomy pouch employing a water-swella- and cold water-insoluble film material has the problem that since its inner-side film layer is water-swella-, complete water resistance cannot be obtained when feces, etc., having a high water content are to be held therein, although it is possible to hold substances with a low water content.

SUMMARY OF THE INVENTION

The present inventor conducted intensive studies in order to eliminate the above-described drawbacks of the prior art products. As a result, it was found that by providing a layer of a fluorine-containing or silicone-type water repellent coating on one side of a water-soluble film or sheet, the coating layer side of
 45 the sheet becomes water-resistant and when water comes into contact with the other side of the sheet, the water penetrates into the sheet and the whole sheet is dispersed in water. The present invention has been completed based on this finding.

Accordingly, an object of the present invention is to provide a multi-layered sheet, one side of which is water-impermeable and serves to prevent the leakage of water or aqueous solutions and the whole of which,
 50 when the other side of the sheet is brought into contact with water, becomes water-dispersible or water-swella- in the presence of water, thereby eliminating the drawbacks of the conventional techniques.

Other objects and effects of the present invention will be apparent from the following description.

The present invention provides a multi-layered sheet comprising a film or sheet substrate which swells in water or is dispersible or soluble in water having formed on one side of the substrate a coating of a
 55 fluorine-containing or silicone-type water repellent.

The characteristic feature of the multi-layered sheet of the present invention resides in that one side of the sheet is water-impermeable and does not allow water or aqueous solutions to leak out but when water comes into contact with the other side of the sheet the whole sheet becomes water-dispersible or water-

swellable. Therefore, the multi-layered sheet of this invention can be used not only in the sanitary material but has applications in many fields, so that it will have a considerable effect on many industries.

DETAILED DESCRIPTION OF THE INVENTION

5 In the present invention, the term "water-swellable" means a property that when a sheet or film is in contact with water, the material expands and gelates as a result of absorbing water, which sheet or film is impossible to maintain its figure under water stream such as stir. On the other hand, the term "water-dispersible" means a property of a sheet or film to disperse in water in the state of being broken into pieces
10 of millimeters or smaller under stream, which material does not absorb water to be distinguishable from water-swellable one. Further, the term "water-soluble" means a property of a sheet or film to completely dissolve in water into liquid state.

The film or sheet material for use as a substrate in this invention is not particularly limited as long as it swells in water or is dispersible or soluble in water. However, a material which is not rendered water-insoluble upon drying or heat treatment after coating should be selected for use as the substrate. Also, the
15 film or sheet material for use as a substrate is not limited in terms of the polymerization degree thereof, as long as a flexible film or sheet is formed thereby. Examples of the film or sheet material for use in this invention include polyvinylpyrrolidone, polyacrylamide, polyvinyl ethers, polyethylene oxide, methyl cellulose, ethyl cellulose, carboxymethyl cellulose, hydroxyethyl cellulose, polyvinyl alcohol, polyacrylic acid
20 and polymethacrylic acid and sodium, potassium, magnesium or calcium salts thereof, isobutene-maleic anhydride copolymers and salts thereof, and the like.

The substrate appropriate for use in the invention preferably has a thickness of 10 to 200 μm , more preferably 20 to 100 μm .

Applications of fluorine-containing water repellents began with their use for the surface treatment of
25 fibers. Since then, water repellents of this type have been used to treat surfaces of various materials. The fluorine-containing water repellent employed in the present invention may be any conventionally utilized one. Examples thereof include products of the emulsion polymerization of tetrafluoroethylene such as polytetrafluoroethylene (PTFE), products of the polymerization of a monomer obtained by incorporating a perfluoroalkyl group of C_1 to C_{20} , preferably C_2 to C_{10} , into the ester group of a methacrylate or obtained
30 by the copolymerization of such a monomer with other monomer(s) obtained by incorporating an alkyl group of C_1 to C_{20} without fluorine atom into the ester group of a methacrylate, products of the polymerization of a perfluorovinyl ether, and the like.

Silicones are materials having excellent weatherability, durability, and unusual surface activity such as water repellency, and they have been utilized, like fluorine-containing water repellents, as fiber-treating
35 agents in various fields. Examples of the silicone-type water repellent for use in this invention include those containing a silicone resin as a major component and reactive silicone compounds which contain methylhydroxypolysiloxane as a major component and undergo network formation with the aid of a catalyst, whereby orientation of hydrophobic methyl groups in the resin molecule occurs to increase repellency of the water repellent as a result of crystallization. Examples of the catalyst used for network formation of the
40 reactive silicone compounds include organic acid salts of metals such as lead, tin, zinc, cobalt, manganese, chromium, zirconium and titanium.

The coating layer of the water repellent preferably has a thickness of 0.2 to 10 μm , more preferably 0.5 to 5 μm .

In the case where the water repellent used for producing the multi-layered sheet of this invention is of
45 the aqueous emulsion type, application of this water repellent to a film or sheet may result in breakage of the film or sheet at the time of coating. For this reason, use of a solvent-based water repellent is preferred, which contains a fluorine series resin or a silicone series resin in an amount of 0.1 to 80 %, preferably 1 to 50 %, based on the total weight, being dissolved in an organic solvent such as 1,1,1-trichloroethane, trichlorotrifluoroethane, ethyl acetate, n-butyl acetate, acetone, methylethyl ketone, methylisobutyl ketone,
50 dioxane, tetrahydrofuran, toluene, xylene, n-hexane, ethanol, butanol, etc.

The multi-layered sheet of the present invention can be easily produced by coating the above-described water repellent using any conventional known technique on one side of a film or sheet which swells in water or is dispersible or soluble in water, drying it in air at a room temperature to 100 °C and heating the same in air at 100 to 150 °C for 1 to 30 min. Thus heat treatment results in orientation of water
55 repellent resin molecule to increase repellent effect.

If the strength of this multi-layered sheet alone is insufficient for a particular application, a nonwoven, woven, or knit fabric made from a material having good dispersibility in water, such as carboxymethyl cellulose, may be used as a reinforcing material for the sheet on the side opposite to the side coated with

the water repellent material.

The multi-layered sheet of this invention can be used for producing a sanitary material such as a disposable diaper, a sanitary napkin, or the like, in which case the multi-layered sheet is used with the water repellent-coated side being in contact with the body. Moreover, it can also be used for manufacturing a portable urine bag or an ostomy bag, with the water repellent-coated side of the sheet being inside. A sanitary napkin employing the multi-layered sheet of this invention and an absorption layer superposed on the water repellent-coated side of the sheet has been ascertained to have significantly improved usability as compared with conventional ones and to show excellent effects, because the multi-layered sheet functions as a leakage-preventive material and it can then be dispersed or swelled in water when the sanitary napkin is discarded.

Although the coating side of the multi-layered sheet of this invention is insoluble in water at ordinary temperature or at a temperature around body temperature, the substrate material is dissolved, dispersed or swelled in water below about 40 °C when water penetrates into the sheet from the side which has no coating.

The present invention is explained below in more detail with reference to the following examples, which should not be construed as limiting the scope of the invention.

EXAMPLE 1

In 100 ml of water there was dissolved 15 g of a polyvinyl alcohol (polymerization degree: 1,800, saponification degree: 87 to 88 %)(UP-180, manufactured by Unitika Ltd., Japan). This solution was cast on a glass plate and dried in air at 40 °C for one night. Over the whole surface of one side of the thus-obtained film (thickness: about 100 µm) which had an area of 100 cm², 0.6 ml of a fluorine-containing water repellent (trade name Asahi Guard AG-650, manufactured by Asahi Glass Co., Ltd., Japan) was coated by using coating-rod to yield a thin layer with a thickness of about 2 µm. The resulting sheet was dried in air at 30-40 °C for about one hour and then heat-treated at about 100-110 °C for 10 minutes. The thus-obtained multi-layered sheet was fabricated into a bag by heat seal method in such a manner that the coating side of the sheet faced inside.

COMPARATIVE EXAMPLE 1

The same procedures as in Example 1 were repeated except that the polyvinyl alcohol film was heat-treated at about 100-110 °C for about 10 minutes without coating a layer of the water repellent.

EXAMPLE 2

The same procedures as in Example 1 were repeated except that the polyvinyl alcohol (UP-180) was replaced with another polyvinyl alcohol (polymerization degree: 1,700, saponification degree: 95.5 to 97.5 %)(UF-170M, manufactured by Unitika Ltd.).

COMPARATIVE EXAMPLE 2

The same procedures as in Example 2 were repeated except that the polyvinyl alcohol film was heat-treated at about 100-110 °C for about 10 minutes without coating a layer of the water repellent.

EXAMPLE 3

The same procedures as in Example 1 were repeated except that the polyvinyl alcohol (UP-180) was replaced with another polyvinyl alcohol (polymerization degree: 1,800, saponification degree: 87 to 89 %)(E-180, manufactured by Unitika Ltd.).

COMPARATIVE EXAMPLE 3

The same procedures as in Example 3 were repeated except that the polyvinyl alcohol film was heat-treated at about 100-110 °C for about 10 minutes without coating a layer of the water repellent.

EXAMPLE 4

The same procedures as in Example 1 were repeated except that the water repellent (AG-650) was replaced with another fluorine-containing water repellent (Asahi Guard AG-610, manufactured by Asahi Glass Co., Ltd.).

5 EXAMPLE 5

The same procedures as in Example 1 were repeated except that the water repellent (AG-650) was replaced with another silicone-type and solvent-based water repellent (POLON-T, manufactured by Shin-Etsu Chemical Co., Ltd., Japan).

10 REFERENCE EXAMPLE

Into each of the bags obtained in Examples 1 to 5 and Comparative Examples 1 to 3 was placed 30 ml of distilled water. The resulting bags were examined for any changes. The results obtained are summarized in Table 1.

Further, a 10 cm square portion of each of the sheets was added to 500 ml of distilled water. While the resulting water was being stirred, the squares were examined for any changes. The results obtained are summarized in Table 2.

20 Table 1

	Water retention in bags
Example 1	No leakage for 1 day or more
Example 2	No leakage for 1 day or more
Example 3	No leakage for 1 day or more
Example 4	No leakage for 1 day or more
Example 5	Leakage in 1 hr.
Comp. Example 1	Leakage in 2 min.
Comp. Example 2	Leakage in 2 min.
Comp. Example 3	Leakage in 2 min.

35 Table 2

	Solubility
Example 1	Dispersed in 20 min.
Example 2	Dispersed in 30 min.
Example 3	Dispersed in 60 min.
Example 4	Dispersed in 20 min.
Example 5	Dispersed in 20 min.
Comp. Example 1	Dissolved in 5 min.
Comp. Example 2	Dissolved in 5 min.
Comp. Example 3	Dissolved in 5 min.

As is apparent from Tables 1 and 2, all of the multi-layered sheets of this invention obtained in the above Examples showed sufficient water retention and solubility.

While the invention has been described in detail and with reference to specific embodiments thereof, it will be apparent to one skilled in the art that various changes and modifications can be made therein without departing from the spirit and scope thereof.

55 Claims

1. A multi-layered sheet comprising a film substrate or sheet substrate which swells, disperses or dissolves in water, which has a fluorine-type or silicone-type water repellent coated on one side of the substrate.

2. The multi-layered sheet as in claim 1, wherein said substrate is a film or sheet of any of polyvinylpyrrolidone, polyacrylamide, polyvinyl ethers, polyethylene oxide, methyl cellulose, ethyl cellulose, carboxymethyl cellulose, hydroxyethyl cellulose, polyvinyl alcohol, polyacrylic acid and polymethacrylic acid and salts thereof, isobutene-maleic anhydride copolymers and salts thereof.
- 5 3. The multi-layered sheet as in claim 2, wherein said substrate is a film or sheet of polyvinyl alcohol.
4. The multi-layered sheet as in claim 1, wherein said fluorine-type water repellent is selected from products of the emulsion polymerization of tetrafluoroethylene, products of the polymerization of a monomer obtained by incorporating a perfluoroalkyl group into the ester group of a methacrylate or
10 obtained by the copolymerization of such a monomer with other monomer(s), and products of the polymerization of a perfluorovinyl ether.
5. The multi-layered sheet as in claim 1, wherein said silicone-type water repellent is compounds containing a silicone resin as a major component or reactive silicone compounds which contain methylhydroxypolysiloxane as a major component and undergo network formation with the aid of a catalyst.
15
6. The multi-layered sheet as in claim 1, wherein said water repellent is a solvent-based water repellent.
20
- 25
- 30
- 35
- 40
- 45
- 50
- 55



12

EUROPEAN PATENT APPLICATION

21 Application number: **91108884.7**

22 Date of filing: **31.05.91**

51 Int. Cl. 5: **C08J 7/04, C09D 127/18,
C09D 129/10, C09D 133/16,
C09D 183/04, //A61L15/00,
C08L101:02, C08L29:04**

30 Priority: **01.06.90 JP 144934/90**

43 Date of publication of application:
18.12.91 Bulletin 91/51

84 Designated Contracting States:
DE FR GB

88 Date of deferred publication of the search report:
02.09.92 Bulletin 92/36

71 Applicant: **UNITIKA LTD.**
No. 50, Higashihonmachi 1-chome
Amagasaki-shi Hyogo(JP)

72 Inventor: **Umemura, Yoshihiro, c/o Unitika Ltd.**
Central Research Institute, 23, Uji Kozakura
Uji-shi, Kyoto(JP)

74 Representative: **Hansen, Bernd, Dr.**
Dipl.-Chem. et al
Hoffmann, Eitle & Partner Patent- und
Rechtsanwälte Arabellastrasse 4 Postfach
81 04 20
W-8000 München 81(DE)

54 Multi-layered sheet.

57 A multi-layered sheet is disclosed, comprising a film substrate or sheet substrate which swells, disperses or dissolves in water, which has a fluorine-type or silicone-type water repellent coated on one side of the substrate.

EP 0 461 484 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 91 10 8884

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 5)
X	DATABASE WPIL, AN=89-297756 (41), Derwent Publications Limited, London, GB; & JP-A-1 221 240 (KURARAY K.K.) * Abstract *	1-3	C 08 J 7/04 C 09 D 127/18 C 09 D 129/10 C 09 D 133/16 C 09 D 183/04 //
Y	IDEM. ---	1-4, 6	A 61 L 15/00
X, Y	DATABASE WPI, AN=79-88531B (49), Derwent Publications Limited, London, GB; & JP-A-54 139 679 (NIPPON SYNTH. CHEM. IND.) * Abstract *	1-4, 6	C 08 L 101:02 C 08 L 29:04
X	EP-A-0 079 248 (UNILEVER) * Claims 1-3, 6-9; page 4, line 19 - page 5, line 11 *	1-4	
Y	---	1-4, 6	
X	GB-A-2 083 762 (ENAK LTD) * Claims 1-5 *	1-3, 5	
A	GB-A-1 388 489 (WACKER CHEMIE) * Claim 1; page 5, lines 81-112 *	1, 5, 6	
			TECHNICAL FIELDS SEARCHED (Int. Cl. 5)
			C 08 J C 09 D
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 17-06-1992	Examiner HALLEMEESCH A.D.
CATEGORY OF CITED DOCUMENTS			
T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ----- & : member of the same patent family, corresponding document			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document			



European Patent
Office

CLAIMS INCURRING FEES

The present European patent application comprised at the time of filing more than ten claims.

- ☐ All claims fees have been paid within the prescribed time limit. The present European search report has been drawn up for all claims.
- ☐ Only part of the claims fees have been paid within the prescribed time limit. The present European search report has been drawn up for the first ten claims and for those claims for which claims fees have been paid,
namely claims:
- ☐ No claims fees have been paid within the prescribed time limit. The present European search report has been drawn up for the first ten claims.

LACK OF UNITY OF INVENTION

The Search Division considers that the present European patent application does not comply with the requirement of unity of invention and relates to several inventions or groups of inventions,
namely:

see sheet -B-

- ☒ All further search fees have been paid within the fixed time limit. The present European search report has been drawn up for all claims.
- ☐ Only part of the further search fees have been paid within the fixed time limit. The present European search report has been drawn up for those parts of the European patent application which relate to the inventions in respect of which search fees have been paid,
namely claims:
- ☐ None of the further search fees has been paid within the fixed time limit. The present European search report has been drawn up for those parts of the European patent application which relate to the invention first mentioned in the claims,
namely claims:



European Patent
Office

EP 91 10 8884

-B-

LACK OF UNITY OF INVENTION

The Search Division considers that the present European patent application does not comply with the requirement of unity of invention and relates to several inventions or groups of inventions, namely:

A Posteriori

1. Claims 1-4,6
2. Claim 5